

Technical Commercial data Sheet

Master

Waterproofing bitumen polymer membrane



Dimensional features

Length	10 m - 1% (UNI EN 1848-1)	Toll. ≥
Width	1 m - 1% (UNI EN 1848-1)	Toll. ≥
Thickness	2/3/4 mm (UNI EN 1849-1)	Tol. 10%
Weight/m ² (MINERAL)	4 /4,5 kg (UNI EN 1849-1)	Tol. 10%

Description

The membranes of the MASTER range are realized with an elastoplastomeric compound with a -5°C cold flexibility and are reinforced in glass tissue or strengthened polyester.

MASTER 4 MM P is also available in the "TEX" version with "DECOTEX" treatment, consisting in the application on the upper face of a special black polypropylenic tissue.

Application

- Use Personal Protective Equipment as requested by law;
- Clean properly the surface on which membranes has to be applied;
- MASTER is meant to be applied by flame with a gas propane blow torch by heating the lower face, covered with a special thermofusible film;
- Apply between +5° C and + 35° C.

Recommended Use

MASTER membranes can be employed on structures of any type, as base layers, top layers, basement structures and foundations. MASTER 4 MM P (if properly protected with specific paint) and MASTER MINERAL versions can be used as top layer.

Storage

It is advisable to keep the rolls in warehouse, not exposed to the sun rays and at a higher temperature than +5°C. Keep the rolls in the upright position. If possible, avoid stacking pallets, especially with slated membranes. It is advisable to use the product within 2/3 months from delivery.

TYPE	REINFORCEMENT	UPPER FACING	THICKNESS WEIGHT/m ²	m ² PER PALLET
MASTER 2 MMV	Glass tissue	Sand	2 mm	480
MASTER 3 MMV	Glass tissue	Sand	3 mm	250
MASTER 4 MM V	Glass tissue	Sand	4 mm	230
MASTER 3 MM P	Polyester	Sand	3 mm	250
MASTER 4 MM P	Polyester	Sand	4 mm	230
MASTER 4 MM P TEX	Polyester	Polypropylene TNT	4 mm	230
MASTER MINERAL 4 KG P	Polyester	Slate	4 kg	250
MASTER MINERAL 4,5 KG P	Polyester	Slate	4,5 kg	230



Isover Saint-Gobain
è socio ordinario
del GBC Italia

CODE: STCBE 119
REVISION: 06
DATE: april 2016
PAGE: 1/2



Saint-Gobain PPC Italia S.p.A. – Brand Isover
Headquarters: Via Ettore Romagnoli, 6 – 20146 Milano

Bituver Plant: Via G.Pastore, 15 - 66013 Chieti Scalo (CH) - Tel. +39 0871/599022 – Fax +39 0871/ 552483

www.bituver.com



Technical Commercial data Sheet

Master

TEST	Standard Reference	MASTER V	MASTER P	MASTER P MINERAL	TOLERANCE
Visible Faults	UNI EN 1850-1	absent	absent	absent	-
Straightness	UNI EN 1848-1	10 mm	10 mm	10 mm	≤
Water tightness	UNI EN 1928	60 kPa	60 kPa	60 kPa	≥
Cold flexibility	UNI EN 1109	- 5 °C	- 5 °C	- 5 °C	≤
L dimensional stability	UNI EN 1107-1	NPD	- 0,3 %	- 0,3 %	≥
Flow resistance	EN 1110	120 °C	120 °C	120 °C	≥
Flow resistance after ageing	UNI EN 1296 UNI EN 1110	110 °C	110 °C	110 °C	- 10 °C
Tensile strength at breaking L/T	UNI EN 12311-1	300 N/5 cm 200 N/5 cm	400/250 N/50 mm	400/250 N/50 mm	- 20 %
Elongation at breaking L/T	UNI EN 12311-1	2% / 2%	35/35 %	35/35 %	- 15 a. v. (P)
Tear resistance (B method) L/T	UNI EN 12310-1	70 N 70 N	130/130 N	130/130 N	- 30 %
Static load resistance	UNI EN 12730	NPD	10 Kg	10 Kg	≥
Dynamic punching resistance	UNI EN 12691	NPD	700 mm	700 mm	≥
Vapour permeability	UNI EN 1931	μ 20000	μ 20000	μ 20000	-
UV ageing	UNI EN 1297	-	Passes the test (4 mm)	-	-
Fire reaction	EN 13501-1	NPD	NPD	NPD	-
External fire reaction	EN 13501-5	F roof	F roof	F roof	-
Granules adhesion	UNI EN 12039	-	-	30%	-
Watertightness after exposure to chemical agents artificial ageing	UNI EN 1928 UNI EN 1847/ UNI EN 1296	NPD	NPD	-	-
Resistance to water penetration	UNI EN 1928	-	-	CLASS W1	-
Res. to water penetration Tensile properties after artificial ageing	App. C EN 13859-1	-	-	NPD	-
Uses	EN 13707 System 2+	Base layer Middle Layer Top layer	Base layer Middle layer Top layer (4 mm)	Top layer	-
	EN 13969 System 2+	Foundations Earth retention	Foundations Earth retention	-	-
	EN 13859-1 System 4		-	Under tiles	-

The Saint-Gobain PPC Italia S.p.A. quality system is certified according to EN ISO 9001

Follow proper application and storage modalities.

The CE marking of this bituminous membrane is in accordance with the European Construction Products Regulation 305/2011, is in agreement to the reference technical standards and is supported by certification no. 1370-CPR-0050.

Saint Gobain PPC Italia has the right to change the technical data of this data sheet any time with no need of notice.



Isover Saint-Gobain
è socio ordinario
del GBC Italia

CODE: STCBE 119
REVISION: 06
DATE: april 2016
PAGE: 1/2



Saint-Gobain PPC Italia S.p.A. – Brand Isover
Headquarters: Via Ettore Romagnoli, 6 – 20146 Milano
Bituver Plant: Via G.Pastore, 15 - 66013 Chieti Scalo (CH) - Tel. +39 0871/599022 – Fax +39 0871/ 552483
www.bituver.com

