

# Technical Commercial data Sheet

## Polimat

### Waterproofing bitumen polymer membrane



#### Dimensional features

Length	10 m - 1% (UNI EN 1848-1)	Toll. ≥
Width	1 m - 1% (UNI EN 1848-1)	Toll. ≥
Thickness	4 mm (UNI EN 1849-1)	Toll. 0,4 mm

#### Description

POLIMAT membranes are realized with elastoplastomeric (BPP) compound that reaches  $-10^{\circ}\text{C}$  cold flexibility. The reinforcement is made by glass tissue or polyester that is strengthened with glass fiber threads.

POLIMAT 4 MM P is also available in the "TEX" version with "DECOTEX" treatment, consisting in the application on the upper face of a special black polypropylene tissue.

#### Application

- Use Personal Protective Equipment as requested by law;
- Clean properly the surface on which membranes has to be applied;
- The treatment of the application surface with Bituver ECOPRIVER water based bituminous primer is suggested;
- POLIMAT is meant to be applied by flame with a gas propane blow torch by heating the lower face, covered with a special termofusibile film;
- Apply between  $+5^{\circ}\text{C}$  and  $+35^{\circ}\text{C}$ .

#### Recommended Use

POLIMAT membranes can be used on all type of structures as base layers, intermediate layers, earth retention and foundation. POLIMAT 4 MM P and POLIMAT MINERAL can be used also as top layers.

#### Storage

It is advisable to keep the rolls in warehouse, not exposed to the sun rays and at a higher temperature than  $+5^{\circ}\text{C}$ . Keep the rolls in the upright position. If possible, avoid stacking pallets, especially with slated membranes. It is advisable to use the product within 2/3 months from delivery.

TYPE	REINFORCEMENT	UPPER FACING	THICKNESS WEIGHT/m <sup>2</sup>	m <sup>2</sup> PER PALLET
POLIMAT 3 MM V	Glass tissue	Sand	3 mm	250
POLIMAT 4 MM V	Glass tissue	Sand	4 mm	230
POLIMAT 3 MM P	Polyester	Sand	3 mm	250
POLIMAT 4 MM P	Polyester	Sand	4 mm	230
POLIMAT 4 MM P TEX	Polyester	Polypropylene TNT	4 mm	230
POLIMAT MINERAL 4 KG P	Polyester	Slate	4 kg	250
POLIMAT MINERAL 4,5 KG P	Polyester	Slate	4,5 kg	230



CODICE: STCBE 009  
REVISIONE: 05  
DATA: april 2016  
Pag. 1 di 2



Saint-Gobain PPC Italia S.p.A. – Attività Isover

Headquarters: Via Ettore Romagnoli, 6 – 20146 Milano

Bituver Plant: Via G.Pastore, 15 - 66013 Chieti Scalo (CH) - Tel. +39 0871/588021 - Fax +39 0871/ 552483

[www.bituver.com](http://www.bituver.com)



# Technical Commercial data Sheet

## Polimat

Test	Standard Reference	POLIMAT V	POLIMAT P	POLIMAT MINERAL P	Tolerance
Visible Faults	UNI EN 1850-1	absent	absent	absent	-
Straightness	UNI EN 1848-1	10 mm	10 mm	10 mm	≤
Water tightness	UNI EN 1928	60 kPa	60 kPa	60 kPa	≥
Cold flexibility	UNI EN 1109	- 10 °C	- 10 °C	- 10 °C	≤
L dimensional stability	UNI EN 1107-1	NPD	- 0,3 %	- 0,3 %	≥
Flow resistance	EN 1110	120 °C	120 °C	120 °C	≥
Flow resistance after ageing	UNI EN 1296 UNI EN 1110	110 °C	110 °C	110 °C	- 10 °C
Tensile strength at breaking L/T	UNI EN 12311-1	300/200 N/50 mm	500/400 N/50 mm	500/400 N/50 mm	- 20 %
Elongation at breaking L/T	UNI EN 12311-1	2/2 %	35/35 %	35/35 %	- 15 a. v. (P) - 2 a. v. (V)
Tear resistance (B method) L/T	UNI EN 12310-1	70/70 N	140/140 N	140/140 N	- 30 %
Static load resistance	UNI EN 12730	NPD	10 Kg	10 Kg	≥
Dynamic punching resistance	UNI EN 12691	NPD	800 mm	800 mm	≥
Vapour permeability	UNI EN 1931	μ 20000	μ 20000	μ 20000	-
UV ageing	UNI EN 1297	-	Passes the test (4 mm)	-	-
Fire reaction	EN 13501-1	NPD	NPD	NPD	-
External fire reaction	EN 13501-5	F roof	F roof	F roof	-
Granules adhesion	UNI EN 12039	-	-	30%	≤
Water tightness after exposure to chemical agents artificial ageing	UNI EN 1928 UNI EN 1847/ UNI EN 1296	NPD	NPD	-	-
Resistance to water penetration	UNI EN 1928	-	-	CLASS W1	-
Res. to water penetration Tensile properties after artificial ageing	App. C EN 13859-1	-	-	NPD	-
Uses	EN 13707 System 2+	Base layer Middle layer	Base layer Middle layer Top layer Heavy protection	Top layer	-
	EN 13969 System 2+	Foundation Earth retention	Foundation Earth retention	-	-
	EN 13859-1 System 4	-	-	Under tiles	-

The Saint-Gobain PPC Italia S.p.A. quality system is certified according to EN ISO 9001

Follow proper application and storage modalities.

The CE marking of this bituminous membrane is in accordance with the European Construction Products Regulation 305/2011, is in agreement to the reference technical standards and is supported by certification no. 1370-CPR-0050.

Saint Gobain PPC Italia has the right to change the technical data of this data sheet any time with no need of notice.



CODICE: STCBE 009  
REVISIONE: 05  
DATA: april 2016  
Pag. 2 di 2

